

Technical Data Sheet



NAUE GmbH & Co. KG
Gewerbestr. 2
32339 Espelkamp-Fiestel
Germany



NAUE Asia Sdn. Bhd.
Lot 8599, Batu 11, Jalan Segenting
42500 Telok Panglima Garang
Selangor, Darul Ehsan
Malaysia

Secutex®

Soft Rock RS 1201

Phone: +49 5743 41-0 Fax: +49 5743 41-240
E-Mail: info@naue.com Internet: www.naue.com

Product description: Secutex® Soft Rock is a geotextile sand container to provide a multi-functional construction element for coastal hydraulic engineering applied as filter, erosion control and scour protection element. These geotextile sand containers (GSC) are made of a double-layered, robust and abrasion resistant needle-punched nonwoven composite, closed along three sides. One side is left open completely for closing on-site with hand-sewing machines.

Property	Test method*	Unit			
Geotextile, polypropylene		(Secutex RS 1201)			
Raw material (filter layer)	-	-	UV-stabilized polypropylene (PP), white		
Raw material (protection layer)	-	-	polypropylene (PP), beige		
Mass per unit area (total product)	EN ISO 9864 / EN 965	g/m ²	1,200		
Mass per unit area (filter layer)	EN ISO 9864 / EN 965	g/m ²	approx. 600		
Mass per unit area (protection layer)	EN ISO 9864 / EN 965	g/m ²	approx. 600		
Thickness	EN ISO 9863-1 / EN 964-1	mm	8.0		
Max. tensile strength, md/cmd	EN ISO 10319	kN/m	34.0 / 48.0		
Elongation at max. tensile strength, md/cmd	EN ISO 10319	%	60 / 30		
CBR puncture	EN ISO 12236	N	7,500		
Characteristic opening size	EN ISO 12956	µm	80		
Water permeability	EN ISO 11058	m/s	2.5 x 10 ⁻²		
- V _{H50} -Index			l/(s m ²)	25	
- Flow rate _{H50}					
Geotextile container condition upon delivery (empty):					
Raw material, overlock stitch	-	-	polypropylen (PP)		
Tensile strength of the factory-made seam	EN ISO 10321	kN/m	40.0		
Available finished outer dimensions, width / length	-	m x m	1.45 x 2.38	1.45 x 3.18	1.90 x 2.78
Available filling volume	-	m ³	approx. 1.0	approx. 1.5	approx. 2.0
Geotextile container in filled condition					
The dimension and the weight may vary depending on the installation density of the filling material, filling method, handling and installation specific factors.					

*based on

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.