

Fibre-reinforced Geosynthetic Clay Liner (GBR-C)

Bentofix® B 5100 c

New Zealand

Bentofix® B 5100 c is a shear strength transmitting geosynthetic clay barrier (GBR-C), continuously needle-punched through all components. A GBR-C is also known as geosynthetic clay liner (GCL) or bentonite mat. Additional bentonite powder is impregnated into a 500 mm overlapping area on both longitudinal sides of the cover layer. The 300 mm length longitudinal overlapping areas are marked on the carrier layer. The geotextile layers meet the requirements according to ISO/TS 13434 of at least 100-year service lives.

Property	Test method*	Unit	Value
Geotextile layers:			
Cover layer (polypropylene nonwoven):			
Mass per unit area	ASTM D5261	g/m ²	≥ 200
Carrier layer (polypropylene nonwoven-woven composite):			
Mass per unit area	ASTM D5261	g/m ²	≥ 240
Bentonite layer (sodium bentonite powder):			
Mass per unit area	ASTM D5993 ($\rho_{\text{CLAY, 0\%}}$)	g/m ²	≥ 3,700
Swell index	ASTM D5890	ml/2g	≥ 24
Fluid Loss	ASTM D5891	ml	≤ 18
Moisture content	ISO 11465 (5hrs, 105 °C)	%	≤ 15
Carbonate content	XRD	% wt	1-2
Particle size, passing a 75µm sieve	Dry screen	%	> 80
Cation exchange capacity	Methylene blue method	meq/100 g	≥ 70
Montmorillonite content	VDP69 (Methylene blue)	mg/g	≥ 300
Geosynthetic Clay Liner:			
Mass per unit area	ASTM D5993 ($\rho_{\text{GBR-C, 0\%}}$)	g/m ²	≥ 4,140
Thickness	ASTM D 5199	mm	≥ 6.3
Tensile strength, md/cmd**	EN ISO 10319 / ASTM D6768	kN/m	≥ 10.8 / ≥ 18.0
Elongation at max. strength, md/cmd**	EN ISO 10319 / ASTM D6768	%	≥ 45.0 / ≥ 27.0
Peel strength	ASTM D6496	N/m	≥ 360
Static puncture (CBR), strength***	ASTM D6241	N	≥ 3,000
Hydrated internal shear strength (maximum peak @10 kPa normal stress)	ASTM D6243	kPa	≥ 35
Hydrated internal shear strength (maximum peak @ 30 kPa normal stress)	ASTM D6243	kPa	≥ 50
Hydraulic Conductivity (k_{10})	EN 16416 / ASTM D5887	m/s	≤ 3.0 x 10 ⁻¹¹
Index Flux (q_{10})	EN 16416 / ASTM D5887	(m ³ /m ²)/s	≤ 5.8 x 10 ⁻⁹
Roll dimensions:			
width x length, / diameter (approx.)	-	m x m / m	5.00 x 40 / 0.60

* = based on; **md = machine direction, cmd = cross machine direction, *** = The highest peak will be evaluated

The listed technical values are either minimum values (≥) or maximum values (≤), achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.